


Modified reissue
**Report of the classification of the reaction to
fire performance**

No. 230008744-9
issued 21 December 2022
English version

Sponsor



Order

Classification of the reaction to fire behaviour according to DIN EN 13501-1

Date of order:

9 October 2012, 22 January 2013, 17 August 2017 and 31 October 2022

Name of the classified building product

Flexible foam boards „Basotect G+“ in thicknesses of 5 mm to 15 mm

This report determines the classification of the above-mentioned building product in accordance with the procedure given in DIN EN 13501-1.

Publishing and copying of classification reports without permission of MPA NRW is only allowed without any changes of the content and the form of the reports.

A shortened reproduction of a certification report needs the permission of MPA NRW.

This classification report consists of 4 pages.

MPA NRW is a notified body with the identification no. 0432.

1. Description of the building product

Flexible foam boards named „Basotect G+“.



Thickness: 5 mm – 15 mm

Density: approx. 9 kg/m³


Colour: grey

2. Test reports and test results which form the basis of the classification

2.1 Test reports

Name of the laboratory	Sponsor	Number of the test report	Test method
MPA NRW		230008744-8 of 15 Feb. 2013	DIN EN 13823
MPA NRW		230008744-4 of 29 Nov.2012	DIN EN ISO 11925-2

Indication 1: This modified reissue of the classification report is based on indicative tests, the results of which are documented in the following test report.

Name of the laboratory	Sponsor	Number of the test report	Test method
MPA NRW		231001744-1 of 21 Dec. 2022	DIN EN 13823

Indication 2: The results of these indicative tests confirm the classification of the product described in section 1.

2.2 Test results

Test method	Number of tests	Parameter	Test results	
			Continuous parameter average values	Discrete parameter
DIN EN 13823	4	FIGRA _{0,2} (W/s)	3.7	--
		THR _{600s} (MJ)	0.9	--
		LFS < outer edge	--	yes
		SMOGRA (m ² /s)	26.3	--
		TSP _{600s} (m ²)	33.3	--
		Burning droplets / particles (s)	0	--

Indication 1: The values for SMOGRA and TSP_{600s} were calculated by using the alternative calculation procedure according to DIN EN 13823, remark to clause A.6.1.2.

Test method	Number of tests	Parameter	Test results	
			Continuous parameter average values	Discrete parameter
DIN EN ISO 11925-2	18 x K and 18 x F	F _s ≤ 150 mm	--	yes
		Burning droplets / particles	--	no

Remark: K = tested with flames exposed to the edge, F = tested with flames exposed to the surface

Indication 2: The classification is based on test report nos. 230008744-4 dated 29.11.2012 and 230008744-8 dated 15.02.2013.

3. Classification and direct field of application

3.1 Reference

The classification was carried out in accordance with the clauses 11. and 14.1 of the standard DIN EN 13501-1: 2010.

3.2 Classification

The tested material in relation to its fire behaviour is classified as: **B**

The additional classification regarding the smoke production is: **s1**

The additional classification regarding burning droplets / particles is: **d0**

This results in a classification of the reaction to fire behaviour of the tested material:

Fire behaviour	Smoke production	Burning droplets / particles
B	s1	d0

i.e. **B – s1, d0**

3.3 Field of application of the product

The classification is solely valid for the product described in clause 1 for the following fields of application:


- Directly laid and mechanically fixed onto substrates classified as A1 or A2-s1,d0 with a density of at least 653 kg/m³ and a thickness of at least 9 mm.

4. Restrictions


This classification report does not replace any type approval or certification of the product.

This classification report written in English language is issued additionally to the report written in German language with the same report number. In case of doubt the German version is solely valid. This classification report is only valid in combination with the German version of the report.

Erwitte, 21 December 2022


 Dipl.-Ing. Rademacher
 Head of the testing body




 Dipl.-Ing. Jung
 Official in charge